

SL52125323443101TX

Date:December 09,2021

Page 1 of 6

TAYA CANVAS(SHANGHAI) CO.,LTD NO.777 FENGGUAN ROAD, FENGJING INDUSTRIAL PARK, JINSHAN DISTRICT, SHANGHAI, CHINA

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)Sample (White)

Sample Color : (A)White
Style No. : Sunlight ZeRo

Proposed Care Instruction: -

Sample Receiving Date : Nov 16, 2021

Testing Period : Nov 16, 2021 - Dec 09, 2021

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant

Signed for and on behalf of SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center

Alice Wang (Authorized Signatory)

Alice Wary



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its Intervention only and within the limits of Client's Instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com



SL52125323443101TX

Date:December 09,2021

Page 2 of 6

Test Result:

Flammability test*

Test Requested:

DIN 4102-1:1998-05 Fire behaviour of building materials and elements Part 1: Classification of building materials, Requirements and testing, Class B1 materials---For all materials except flooring.

Classification: The tested sample meets class B1 materials requirements of DIN 4102-1:1998-05.

I. Test conducted

This test was conducted as per DIN 4102-15:1990 Fire behaviour of building materials and elements – 'Brandschacht' apparatus, DIN 4102-16:2015 Fire behaviour of building materials and elements – 'Brandschacht' tests and DIN 4102-1:1998-05 Clause 6.2, and Classification according to DIN 4102-1:1998-05 Clause 6.1 Class B1 materials.

II. Sample details

General description	Fabric
Color	White
Area Density	402 g/m ²
Size of sample	190mm×1000mm & 190mm×90mm

Conditioning

Prior to testing, the sample was conditioned at least 14 days to constant mass at a temperature of 23 \pm 2 °C, and a relative humidity of 50 \pm 5 %.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its Intervention only and within the limits of Client's Instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

3rdBuilding,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 f (86-21) 64958763 t (86-21) 61402666 f (86-21) 64958763



SL52125323443101TX

Date:December 09,2021

Page 3 of 6

III. Test results

1) "Brandschacht" Test according to DIN 4102-15 &16

Exposed surface: Lengthwise and Crosswise face

Results of "Brandschacht" Test (part 1)								
Line		Unit	Test direction					
No.		Offic	Lengthwise	Widthwise				
1	Specimen fixings according to DIN 4102 part 15, table	1	1	1				
2	Max. flame height above lower sample edge;	cm	60	60				
3	Time 1)	min:s	01:02	01:02				
	Melting/burning through		Yes	Yes				
4	Time 1)	min:s	00:04	00:04				
	Back of specimen		Yes	Yes				
5	Flaming/glowing, Time 1)	min:s	00:04	00:04				
6	Discolouring, Time 1)	min:s	00:04	00:04				
	Burning droplets		Yes	Yes				
7	Begin 1)	min:s	00:04	00:05				
	Amount		1	1				
8	Specimen material falling off in separate droplets		√	√				
9	Specimen material falling off continuously		1	1				



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms



SL52125323443101TX

Date:December 09,2021

Page 4 of 6

Results of "Brandschacht" Test (part 2)							
Line			Test direction				
No.			Lengthwise	Widthwise			
	Burning parts		No	No			
10	Begin 1)	min:s	1	1			
11	Parts of sample falling off separately		1	1			
12	Parts of sample falling off continuously		/ /				
13	Duration of continued combustion on mesh base (max.)	min:s	No	No			
	Burner flame impairment by dripping/falling material		No	No			
14	Time 1)	min:s	/	/			
	Premature ending of test		1	1			
15	End of burning at specimen 1)	min:s	1	1			
16	Time when test terminated (if applicable) 1)	min:s	1	1			
	Burning after end of test		No	No			
17	Duration	min:s	1	1			
18	Number of specimens		1	/			
19	Front of specimen		1	/			
20	Back of specimen		1	/			
21	Height of flame	cm	1	/			
	Glowing after end of test		No	No			
22	Duration	min:s	/	/			
23	Number of specimens		1	/			
24	Front of specimen		/	1			
25	Back of specimen		/	1			
26	Top half of specimen		/	1			
27	Bottom half of specimen		1	1			



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rd Building, No. 889, Yishan Road, Xuhui District Shanghai, China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233

t (86-21) 61402666

t (86-21) 61402666 f (86-21) 64958763 f (86-21) 64958763



SL52125323443101TX

Date:December 09,2021

Page 5 of 6

Results of "Brandschacht" Test (part 3)									
Line		Test direction							
No.	L		Lengthwise		Widthwise				
	Residual length		1	1					
28 5	Single results	cm	54	53	57	56			
20	Single results	CITI	52	56	51	55			
29	Average of the single results	cm	54		55				
	Smoke temperature		1		1				
30	Max. of average	$^{\circ}$	149.7		148.5				
31	Time 1)	min:s	04:21		05:06				

Note: 1) time from start of testing

*Reduction in number of test (DIN 4102 Part 16, clause 5.2)

Class B1 materials:

If the residual length measured after the first test is 45cm or greater, further tests are not required.

2) Normal Flammability Test according to DIN 4102-1 Clause 6.2

Edge ignition

Fire application time: 15s

Parameter	Lengthwise					Crosswise				
Falametei		2	3	4	5	6	7	8	9	10
Whether or not flaming extinguished before reach the gauge mark (Yes/No)	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
Whether or not flaming reach the measuring mark within 20 seconds (Yes/No)	No	No	No	No	No	No	No	No	No	No
Time for the flame tip to reach the gauge mark (s)	NA	NA	NA	NA	NA	NA	NA	NA	NA	NA
Afterflame time (s)	0	0	0	0	0	0	0	0	0	0
Max. flame height (cm)	7	7	8	7	6	7	8	7	7	7
Molten dripping (Yes/No)	No	No	No	No	No	No	No	No	No	No
Smoke developments (visual impression)	Slight					Slight				

Note: NA---Not applicable



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rdBuilding,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233

t (86-21) 61402666

t (86-21) 61402666 f (86-21) 64958763 f (86-21) 64958763



SL52125323443101TX

Date:December 09,2021

Page 6 of 6

IV. DIN 4102-1:1998 Criteria for classification

- 1) All materials, except flooring, may be classed as **B1** materials if they meet the following requirements a) and b):
- a) The test using the 'Brandschacht' apparatus described in DIN 4102-15 (cf. subclause 6.1.3.1) shall be deemed passed if
- The mean value for the residual length (portion of specimen that has not burned or charred; cf. subclause
- 9.1 of DIN 4102-16) of each specimen is at least 15 cm and no individual values are lower than 0 cm,
- The mean effluent temperature does not exceed 200 °C in any test,
- The requirement for the residual length of each specimen is met even where there is afterflame, afterglow, or smouldering.
- b) Pass DIN 4102-1:1998 sub-clause 6.2.3 Ignitability Test if

For each specimen, flaming doesn't reach the gage mark within 20s after flame application.

2) Materials may be classed as **B2** materials if they pass the ignitibility test specified in DIN 4102-1:1998 subclause 6.2.5.

For each specimen, flaming doesn't reach the gage mark (150mm marks) within 20s after flame application.

3) Combustible materials which cannot be classed as B1 or B2 materials shall be classed as B3 materials.


STATEMENTS:

This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

This test report does not replace any mandatory certification of the product that may be required.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire and smoke hazard of the product in use.

*This test was carried out by SGS-CSTC Standards Technical Services (Anji) Co., Ltd.



The statement of conformity in this test report is only based on measured values by the laboratory and does not take their uncertainties into consideration

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions of Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Condi

3^{rg} Building,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 t (86-21) 61402666 f (86–21) 64958763 f (86–21) 64958763